

PRODUCT INFORMATION

Material: PC/Polyester Alloy
Grade: PC/TP-GP3
Description: High Impact, Superior Chemical Resistance

Effective Date: June-03

TYPICAL PROPERTIES	VALUE	UNIT	TEST METHOD
Physical*			
Melt Flow Rate 265C/2.16kg	5-15	g/10 min	ASTM D1238
Specific Gravity	1.24		ASTM D792
Mold Shrinkage	13-18	E-3 in/in	ASTM D955
Mechanical*			
Tensile Strength, Break	6,400	psi	ASTM D638
Tensile Strength, Yield	6,700	psi	ASTM D638
Flexural Strength	9,600	psi	ASTM D790
Flexural Modulus	260	psi x 1000	ASTM D790
Impact*			
Notched Izod Impact Strength	15.0	ft-lb/in.	ASTM D256
Gardner Falling Dart Impact (minimum)	320	in-lbs.	ASTM D3029
Thermal*			
HDT @ 66 psi	240	°F	ASTM D648
HDT @ 264 psi	170	°F	ASTM D648
Flammability			
UL File Number, USA	not listed		
UL 94 rating		HB (0.125 in)	
		HB (0.0625 in)	

* All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. tested dry as molded(DAM) and foam grades tested with un-foamed parts.

Nylon grades are

TYPICAL PROCESSING CONDITIONS

Processing Method: Injection Molding

Drying Temperature	220-230	°F	
Drying Time	4-6	Hours	Do not exceed 8 hours
Melt Temperature	460-500	°F	
Mold Temperature	120-180	°F	
Front Zone	460-500	°F	
Middle Zone	450-480	°F	
Rear Zone	440-470	°F	

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make his own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.