

Teijin Kasei America, Inc.



Friday, August 31, 2007

Panlite® LN-2250Y

Teijin Kasei America, Inc. (Teijin Chemicals) - Polycarbonate

Unit System: **Actions****Legend (Open)****General Information****General**

Material Status	Commercial: Active	
Availability	Asia Europe North America	
Test Standards Available	ASTM ISO	
Features	Flame Retardant Mold Release, Good Viscosity, Low	
Uses	Appliances Electrical/Electronic Applications General Purpose	Lighting Fixtures Parts, Transparent or Translucent
Appearance	Clear	
Forms	Pellets	
Processing Method	Injection Molding	

ASTM and ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density -Specific Gravity	1.20	sp gr 23/23°C	ASTM D792
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	0.671	in ³ /10min	ISO 1133
Mold Shrink, Linear-Flow	0.0050 to 0.0070	in/in	ASTM D955
Mold Shrink, Linear-Trans	0.0050 to 0.0070	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
(Across Flow)	0.50 to 0.70	%	
(Flow)	0.50 to 0.70	%	
Water Absorption @ 24 hrs (73 °F)	0.20	%	ASTM D570
Water Absorption 24h/23C	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	348000	psi	ISO 527-1, -2
Tensile Strength @ Yield	9280	psi	ASTM D638
Tensile Stress at Yield ³	8850	psi	ISO 527-1, -2
Tensile Strength @ Break	11200	psi	ASTM D638
Tensile Elongation @ Yld	6.0	%	ASTM D638
Tensile Strain at Yield ³	6.0	%	ISO 527-1, -2
Tensile Elongation @ Brk	130	%	ASTM D638
Nominal Tensile Strain at Break ³	50	%	ISO 527-1, -2
Flexural Modulus	329000	psi	ASTM D790
Flexural Modulus ⁴	341000	psi	ISO 178
Flexural Strength ⁴	13300	psi	ISO 178
Flexural Strength @ Yield	13100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.71	ft-lb/in ²	ISO 179
Charpy Unnotched Impact Strength	No Break	ft-lb/in ²	ISO 179
Notched Izod Impact			ASTM D256
(0.126 in)	15.5	ft-lb/in	
(0.252 in)	1.87	ft-lb/in	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	77		ASTM D785
Thermal	Nominal Value	Unit	Test Method
DTUL @66psi - Unannealed	288	°F	ASTM D648
HDT B (0.45 MPa) Unannealed	286	°F	ISO 75B-1, -2
DTUL @264psi - Unannealed	268	°F	ASTM D648

HDT A (1.80 MPa) Unannealed	262 °F	ISO 75A-1, -2
Vicat Softening Temperature (B50 (50°C/h 50N))	298 °F	ISO 306
CLTE, Flow	0.000039 in/in/°F	ASTM D696
Coefficient of Linear Thermal Expansion, Flow	0.000039 in/in/°F	ISO 11359-1, -2
CLTE, Transverse	0.000039 in/in/°F	ASTM D696
Coefficient of Linear Thermal Expansion, Transverse	0.000039 in/in/°F	ISO 11359-1, -2
Electrical	Nominal Value Unit	Test Method
Surface Resistivity	1.0E+15 ohms	IEC 60093
Volume Resistivity	3.0E+18 ohm-cm	ASTM D257
Volume Resistivity	1.0E+15 ohm-cm	IEC 60093
Dielectric Strength (0.0630 in) ⁵	762 V/mil	ASTM D149
Dielectric Constant		ASTM D150
(60 Hz)	2.950	
(1E+6 Hz)	2.900	
Dissipation Factor		ASTM D150
(60 Hz)	0.0040	
(1E+6 Hz)	0.0090	
Dissipation Factor		IEC 60250
(100 Hz)	0.00100	
(1E+6 Hz)	0.00900	
Arc Resistance	100 sec	ASTM D495
Comp Track Index	230 V	IEC 60112
Electric Strength	810 V/mil	IEC 60243-1
Relative Permittivity		IEC 60250
(100 Hz)	3.10	
(1E+6 Hz)	3.00	
Flammability	Nominal Value Unit	Test Method
Flame Rating - UL		UL 94
(0.0169 in)	V-2	
(0.118 in)	V-0	
UL 746	Nominal Value Unit	Test Method
RTI Str (0.118 in)	257 °F	UL 746
RTI Imp (0.118 in)	239 °F	UL 746
RTI Elec (0.118 in)	257 °F	UL 746
Comparative Tracking Index (CTI)	230 V	UL 746
Optical	Nominal Value Unit	Test Method
Refractive Index	1.585	ASTM D542
Transmittance (118 mil)	88.0 %	ASTM D1003
Additional Properties		
Electric Strength, IEC 60243-1, Short Time Test: 32 MV/m		

Notes

- 1 Typical properties: these are not to be construed as specifications.
- 2 0.039 in/min
- 3 2.0 in/min
- 4 0.079 in/min
- 5 Method C (Slow Rate-of-Rise)

Teijin Kasei America, Inc. (770)346-8949



Copyright ©, 2007 [IDES - One Source. Plastics Data.](#)

The information presented on this data sheet was acquired by IDES from various sources, including the producer of the material and recognized testing agencies. In some cases, material updates have been integrated directly into the IDES Plastics Database by the material producer utilizing the [Data Maintenance Tool](#). IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and urges that upon final material selection, data points are validated with the manufacturer.