

**PRODUCT INFORMATION**

Material: Polycarbonate
Grade: PC-UV2-D
Description: UV-stabilized, Medium Flow

Effective Date: June-03

TYPICAL PROPERTIES	VALUE	UNIT	TEST METHOD
Physical*			
Melt Flow Rate 300C/1.2kg	9-16	g/10 min	ASTM D1238
Specific Gravity	1.20		ASTM D792
Mold Shrinkage	5-7	E-3 in/in	ASTM D955
Mechanical*			
Tensile Strength, Break	10,000	psi	ASTM D638
Tensile Strength, Yield	9,000	psi	ASTM D638
Flexural Strength	13,900	psi	ASTM D790
Flexural Modulus	335	psi x 1000	ASTM D790
Impact*			
Notched Izod Impact Strength	15.0	ft-lb/in.	ASTM D256
Gardner Falling Dart Impact (minimum)	320	in-lbs.	ASTM D3029
Thermal*			
HDT @ 66 psi	275	°F	ASTM D648
HDT @ 264 psi	265	°F	ASTM D648
Flammability			
UL File Number, USA	E113219		
UL 94 rating	V-2 (0.125 in)		
	V-2 (0.0625 in)		

* All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.
 tested dry as molded(DAM) and foam grades tested with un-foamed parts.

Nylon grades are

TYPICAL PROCESSING CONDITIONS**Processing Method: Injection Molding**

Drying Temperature	245-255	°F	
Drying Time	3-4	Hours	Do not exceed 8 hours
Melt Temperature	550-600	°F	
Mold Temperature	160-200	°F	
Front Zone	560-600	°F	
Middle Zone	540-580	°F	
Rear Zone	520-560	°F	

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make his own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.