

# PEARLTHANE® 11T80

Thermoplastic Polyurethane Elastomer

PEARLTHANE® 11T80 is a polycaprolactone copolyester based TPU, supplied in form of translucent, colourless or slightly yellowish pellets, combining hardness with excellent mechanical properties as well as an improved transparency. It can be extruded and injection-moulded.

## TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Values *
Density @ 20°C	DIN 53.479	1.16 g/cm <sup>3</sup>
Shore Hardness	DIN 53.505	82 A
Tensile Strength	DIN 53.504	40 MPa
Elongation @ Break	DIN 53.504	630 %
Modulus @ 100% Elongation	DIN 53.504	5 MPa
Modulus @ 300% Elongation	DIN 53.504	8 MPa
Tear Strength	DIN 53.515	80 kN/m
Abrasion Loss	DIN 53.516	20 mm <sup>3</sup>
Compression Set (70 h. @ 23°C)	ASTM D395B	27 %
Compression Set (24 h. @ 70°C)	ASTM D395B	36 %
Moisture Content	MQSA 44	< 0.1 %
Melting Range (MFI=10**)	MQSA 111	176 – 186 °C
Tg (DSC, 10°C / min.)	DIN 51.007	- 45° C

\* These are typical values & should not be used for establishing specifications.

\*\* Temperature at which MFI = 10 g/10 min @ 21.6 kg.

## WORKING INSTRUCTIONS

For optimum results, previous drying of the product during 1-2 hours at 100-110° C is advisable, in a hot air circulatory, vacuum or desiccant-air dryer.


### EXTRUSION

In accordance with our experience, the characteristics of the extruder that are suitable for processing PEARLTHANE® 11T80 are the following ones:

1. L/D ratio between 25:1 and 30:1
2. The extruder screw must have 3 zones and a compression ratio between 2:1 and 3:1 (usually, the screws that are used for Polyethylene extrusion give good results).
3. The extruder screw should have a continuous regulation device and a working power higher than for processing other plastics.
4. The speed of the extruder should be low (12 to 60 rpm, depending on its diameter), so as to avoid material degradation due to shearing.
5. The filters used should be disks with holes of 1.5 to 5 mm. (depending on the screw and the die), and screen packs (the nr. of meshes /cm<sup>2</sup> will depend on the end product that is processed), so as to create a pressure built-up.

**PEARLTHANE® 11T80**  
Thermoplastic Polyurethane Elastomer

The suggested processing-temperature profiles for film extrusion (flat films) are depicted in the figure below  
For optimum results, previous drying of the product during 1-2 hours at 100-110° C is advisable, in a hot air circulatory, vacuum or desiccant-air dryer.



**EXTRUDER & CONDITIONS**  
TYPE.- 30/25D (L/D=25:1), COOLING.- Air, SCREW.- 3:1, SPEED.- 20 rpm.,  
BREAKER PLATE.- --, FILTER PACK.- --, THICKNESS DIE.- 0,2 mm, PRE-DRYING.- 1h @ 105 °C

**INJECTION MOULDING**

Based on an injection moulding equipment with the following characteristics:

Closing force: 30 tons  
Screw diameter: 26 mm  
L/D ratio: 23  
Maximum hydraulic pressure: 210 bar  
Mould: Plaque 120x120x2 mm

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

# PEARLTHANE® 11T80

Thermoplastic Polyurethane Elastomer

The suggested processing conditions are the following ones:

## INJECTION CONDITIONS

Feed zone	190°C	Injection pressure	110 bar
Compression zone	195°C	Injection time	4sec
Metering zone	205°C	Holding pressure	60 bar
Nozzle	210°C	Holding time	15 sec
Mould temperature	35°C	Cooling time	20 sec

*Screw speed: approx. 75 rpm.*

## APPLICATIONS

**PEARLTHANE® 11T80** when extruded, is used for making films, tubing, profiles and a variety of technical components.

When processed by injection moulding, can be used for making automotive parts and technical parts.

## HEALTH AND SAFETY

A safety data sheet on **PEARLTHANE® 11T80** is available, with all information related to safety.

## PACKAGING

**PEARLTHANE® 11T80** is packaged in heat-sealed, moisture proof multi-layer bags of 25 kg net weight made of PE/Aluminium/PE. Bags are shipped on pallets of 750 kg. Additionally, PE-lined cardboard gaylords of 700 kg net weight are available.

## STORAGE

Material received from Merquinsa should be inspected to assure the containers are not damaged during transportation before being stored prior to use. **PEARLTHANE® 11T80** should be kept in a cool (15-25°C) and dry environment prior to being processed. Standard practice of consuming resin on first-in first-out basis should be employed.

For more information, please feel free to contact us at [www.merquinsa.com](http://www.merquinsa.com)