

**PRODUCT INFORMATION**

**Material:** PC/ABS Alloy  
**Grade:** PC/ABS-FR2  
**Description:** Flame Retardant, Higher Flow

**Effective Date:** August-07

TYPICAL PROPERTIES	VALUE	UNIT	TEST METHOD
<b>Physical*</b>			
Melt Flow Rate 250C/5kg	40-60	g/10 min	ASTM D1238
Specific Gravity	1.18		ASTM D792
Mold Shrinkage	4-6	E-3 in/in	ASTM D955
<b>Mechanical*</b>			
Tensile Strength, Break	8,200	psi	ASTM D638
Tensile Strength, Yield	8,400	psi	ASTM D638
Flexural Strength	13,500	psi	ASTM D790
Flexural Modulus	370	psi x 1000	ASTM D790
<b>Impact*</b>			
Notched Izod Impact Strength	10.0	ft-lb/in.	ASTM D256
Gardner Falling Dart Impact (minimum)	320	in-lbs.	ASTM D3029
<b>Thermal*</b>			
HDT @ 66 psi	185	°F	ASTM D648
HDT @ 264 psi	175	°F	ASTM D648
<b>Flammability</b>			
UL File Number, USA	E113219		
UL 94 rating	5VA (0.125 in)		
	V-0 (0.0625 in)		

\* All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded(DAM) and foam grades tested with un-foamed parts.

**TYPICAL PROCESSING CONDITIONS****Processing Method: Injection Molding**

Drying Temperature	170-180	°F	
Drying Time	3-4	Hours	Do not exceed 8 hours
Melt Temperature	475-525	°F	
Mold Temperature	140-180	°F	
Front Zone	470-530	°F	
Middle Zone	450-510	°F	
Rear Zone	430-490	°F	

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make his own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.