



PRODUCT INFORMATION

Material: PC/ABS Alloy
Grade: PC/ABS-GP2
Description: High Flow PC/ABS Alloy

Effective Date: June-03

TYPICAL PROPERTIES	VALUE	UNIT	TEST METHOD
Physical*			
Melt Flow Rate 250C/5kg	15-25	g/10 min	ASTM D1238
Specific Gravity	1.15		ASTM D792
Mold Shrinkage	5-7	E-3 in/in	ASTM D955
Mechanical*			
Tensile Strength, Break	8,150	psi	ASTM D638
Tensile Strength, Yield	8,350	psi	ASTM D638
Flexural Strength	12,000	psi	ASTM D790
Flexural Modulus	330	psi x 1000	ASTM D790
Impact*			
Notched Izod Impact Strength	10.0	ft-lb/in.	ASTM D256
Gardner Falling Dart Impact (minimum)	320	in-lbs.	ASTM D3029
Thermal*			
HDT @ 66 psi	235	°F	ASTM D648
HDT @ 264 psi	210	°F	ASTM D648
Flammability			
UL File Number, USA	not listed		
UL 94 rating		HB (0.125 in)	
		HB (0.0625 in)	

* All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded(DAM) and foam grades tested with un-foamed parts.

TYPICAL PROCESSING CONDITIONS

Processing Method: Injection Molding			
Drying Temperature	170-180	°F	
Drying Time	3-4	Hours	Do not exceed 8 hours
Melt Temperature	525-575	°F	
Mold Temperature	160-200	°F	
Front Zone	500-575	°F	
Middle Zone	490-560	°F	
Rear Zone	480-550	°F	

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply, to all goods supplied by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. The user of this material must make his own evaluations to determine the suitability of this material from a technical as well as a health, safety and environmental standpoint. This data is not intended for specification purposes.